

Artikel: SA 3200-06
 Los: 5190-06
 Stück: 17
 Kunde: Textil GmbH

Datum/Zeit: 30.06.2006, 14:55 - 30.06.2006, 14:56
 Bed. Person: J. Schmidt

Wasserdichtheit - Gradientenmethode

Gradient: 60 mbar/Min
 Prüffläche: 100 cm²


Datum/Zeit: 30.06.2006, 14:55 - 30.06.2006, 14:56
 Instrument: Textest FX 3000-III, S/N: 674

1. Tropfen 3. Tropfen

1:	1'630 mbar	1'770 mbar
2:	1'600 mbar	1'690 mbar
3:	1'790 mbar +	1'860 mbar +
4:	1'550 mbar	1'630 mbar
5:	1'610 mbar	1'760 mbar

Kommentar:

MW:	1'640 mbar	Soll:	1'600 mbar
Min:	1'550 mbar	Min:	1'500 mbar
Max:	1'790 mbar +	Max:	1'700 mbar
CV:	5.6 %	Anzahl:	5
VB:	6.9 %	VB:	3.0 %



MW:	1'740 mbar	Soll:	1'700 mbar
Min:	1'630 mbar	Min:	1'600 mbar
Max:	1'860 mbar +	Max:	1'800 mbar
CV:	5.0 %	Anzahl:	5
VB:	6.2 %	VB:	3.0 %

