

Your company name and address

Test Report no. 2006.07.03, 12.59.25.LBD

 **LBD143**

Style: CMT 4322-200
 Lot: 5360-06
 Piece: 12
 Customer: Textile Ltd

Date/time: 07/03/2006, 12:59 - 07/03/2006, 13:01
 Operator: J. Smith

Tearing Strength - Elmendorf Method

Specimens: 1
 Measuring range: 30000 cN

Date/time: 07/03/2006, 12:59 - 07/03/2006, 13:01
 Instrument: Textest FX 3750, s/n: 346

1:	15'100 cN		
2:	16'500 cN +	««« deleted	skewed tear
2:	14'700 cN		
3:	15'000 cN		
4:	13'800 cN -		
5:	14'700 cN		

Commentary:

Avg:	14'700 cN	Nominal:	15'000 cN
Min:	13'800 cN -	Min:	14'000 cN
Max:	15'100 cN	Max:	16'000 cN
CV:	3.5 %	Tests:	5
CI:	4.3 %	CI:	

